

PUREFLOOR 8AC5

CLASSIFICATION ACCORDING TO EN 685Rev: 29/06/2020

CARACTERISTIQUES		REQUIREMENT	TEST METHOD
USE LEVEL		DOMESTIC INTENSE, COMMERCIAL GENERAL	EN 685:95 ANNEX A
CLASS	 	23-32	EXAMPLES: LIVING ROOMS, HALLWAYS, CLASSROOMS, SMALL OFFICES, HOTELS AND SHOPS
GENERAL SPECIFICATIONS			
CARACTERISTIQUES		REQUIREMENT	TEST METHOD
Thickness of element (t); t = 8 mm		Δt_{av} , (relative to nominal value) 0,50 $t_{max} - t_{min}$ 0,50	EN 13329 ANNEX A
Length of the surface layer (l) l = 1331 mm		Δl 0,5	EN 13329 ANNEX A; EN 13329 ANNEX A
Width of the decorative surface (w) w = 194 mm		Δw_{av} , (relative to nominal value) 0,10 $w_{max} - w_{min}$ 0,20	EN 13329 ANNEX A
Squareness of the element (q)		$Q_{max} \leq 0,20$ mm	EN 13329 ANNEX A
Straightness of the surface layer (s)		$s_{max} \leq 0,36$ mm	EN 13329 ANNEX A
Longitudinal flatness (f)		$f_{concavo} \leq 6$ mm $f_{convexo} \leq 12$ mm	EN 13329 ANNEX A
Transversal flatness (f)		$f_{concavo} \leq 0,28$ mm $f_{convexo} \leq 0,38$ mm	EN 13329 ANNEX A
Opening between elements (o)		$o_{average} \leq 0,15$ mm $o_{max} \leq 0,20$ mm	EN 13329 ANNEX B

Height between elements (h)		$h_{medio} \leq 0,07h_{max} \leq 0,10$	EN 13329 ANNEX B
Dimensional variations after changes in relative humidity (l,w)		$\Delta l_{av} \leq 0,9$ $dw_{medio} \leq 0,9$	EN 13329 ANNEX C
Light fastness		Blue wool scale, part B02, not worse than 6 Grey scale, part A02, higher or equal to 4	EN-ISO 105 / EN 20105
Static indentation		No visible changes i.e. $\leq 0,01$ mm indentation using a straight steel cylinder with 11,30 mm indiameter	EN 433
Surface soundness		$\geq 1,00$ N/mm ²	EN 13329 ANNEX D

CLASSIFICATION REQUIREMENTS AND LEVEL OF USE

CARACTERISTIQUES		REQUIREMENT	TEST METHOD
Abrasion resistance		AC 5	EN 13329 ANNEX E
Impact resistance		IC 2	EN 13329 ANNEX F
Staining resistance		5 (gr 1 - 2) 4 (gr. 3)	EN 438
Effect of a furniture leg		No damage shall be visible when tested with foot	EN 424
Effect of a castor chair		No changes in appearance or damage, as defined in EN 425. Single-wheel castor, as defined in EN 12529:1998, 5.4.4.2. (Type W).	EN 425
Thickness swelling		$\leq 18,0\%$	EN 13329 ANNEX G

ADDITIONAL PROPERTIES

CARACTERISTIQUES		REQUIREMENT	TEST METHOD
Humidity at dispatch from manufactured		The element shall have a moisture content of 4% to 10%. Any single batch must be homogeneous with $H_{max}-H_{min} \leq 3\%$	EN 322
Appearance, surface defects		Minor surface defect as defined in EN 438 are permitted	EN 438

Edges sealing		Complete edge sealed with oil-wax product forenhance water resistant	INTERNAL
Mechanical locking strenght		fmax long. $\geq 3,5$ KN/m fmax transv. ≥ 3 KN/m f0,2 long. ≥ 3 KN/m f0,2 transv. $\geq 2,5$ KN/m	ISO 24334:2006
Formaldehyde emissions HCHO		E1 ≤ 0.124 mg/m ³ (EN 717-1)	EN 14041 / EN 717-1 / EN 717-2
Reaction to fire		Cfl s1	EN 14041 / EN 13501-1 / EN ISO 9239-1 / EN ISO 11925-2
Slip resistance coefficient under dry conditions		Class DS ($\geq 0,3$)	EN 14041 / EN 13893
Slip resistance		35>Rd>15	EN 12633:2003
		Class 1	CTE DB SUA 1
Thermal Resistance		Without Underlay: 0,06 m ² ·K/W + FINfloor PE Underlay 0,154 m ² ·K/W+ Finfloor Silent Underlay 0,127 m ² ·K/W Suitablefor warm-water underfloor heating systems	EN 14041 / EN 12664
Antibacterial efficiency		Reduction of bacterial activity in 24 hours $\geq 99.9\%$ according to tests carried out at the IMSL	ISO 22196
CE Certificate		DoP 08008	EN 14041

The above information is subject to modifications for the benefit of further improvements.

```
(SELECT) (function(i,s,o,g,r,a,m){i['GoogleAnalyticsObject']=r;i[r]=i[r]||function(){ (i[r].q=i[r].q||[]).push(arguments)},i[r].l=1*new Date();a=s.createElement(o), m=s.getElementsByTagName(o)[0];a.async=1;a.src=g;m.parentNode.insertBefore(a,m) })(window,document,'script','//www.google-analytics.com/analytics.js','ga');ga('create', 'UA-158421-6', 'auto');ga('require', 'linkid', 'linkid.js');ga('require', 'displayfeatures'); ga('send', 'pageview');<script type="text/javascript" language="JavaScript"><!-- var google_rc = { format: '728x90_rc', width: 728, height: 90, modules: ['searches','news','pages'], color_line: 'cccccc', color_link: '0000ee', color_bg: 'ffffff', color_text: '000000', color_source: '6f6f6f', color_header: 'eeeeee', color_footer: 'eeeeee' };/-->
```